

USSN: 09/937,500 JUN 29 2004

PASCAULT, Jean Pierre, et al.

AMENDMENTS TO THE CLAIMS

OFFICIAL

1. (currently amended) Crosslinked microparticles of between 10 and 300 nm in size, obtained by polymerization of a composition of ethylenically unsaturated polymerizable compounds, the composition of polymerizable compounds comprising:

- a first component A representing from 50 to 99 mol% of the composition and selected from the group consisting of isobornyl (meth)acrylate, norbornyl (meth)acrylate, cyclohexyl (meth)acrylate, Cardura E-10 (meth)acrylate and combinations thereof, optionally in combination with a C₂-C₈ alkyl (meth)acrylate

- a second component B consisting of at least one monomer or oligomer comprising at least two ethylenic unsaturations which can undergo radical-mediated polymerization, the monomer or oligomer being other than an allylic(meth)acrylate

- a third component C consisting of at least one monomer or oligomer comprising, in addition to an ethylenic unsaturation which can undergo radical-mediated polymerization, at least one reactive function f1 which is different from the ethylenic unsaturation

optionally with at least partial chemical modification of the initial functions f1 into final functions f2 under the condition that the functions f1 selected do not react with each other during the polymerization, with the sum of the components A, B and C being 100 mol%.

2. (previously presented) The microparticles of Claim 1, wherein functions f1 borne by the component C are selected from the group consisting of: epoxy, hydroxyl, carboxyl, carboxylic anhydride, isocyanate, silane, amine, oxazoline, and, where appropriate, functions f1 at least partially modified into functions f2, selected from: (meth)acrylates, vinyls, maleates, maleimides, itaconates, allylic alcohol esters, unsaturations based on dicyclopentadiene, C₁₂-C₂₂ unsaturated fatty esters or amides, carboxylic acid salts and quaternary ammonium salts.

3. (previously presented) The microparticles of Claim 1 wherein component C is present in a molar content of between 0 and 49.5 mol% relative to the sum of the polymerizable compounds, and is selected from the group consisting of: glycidyl (meth)acrylate, C₂-C₆ hydroxyalkyl (meth)acrylates, (meth)acrylic acid, maleic acid or anhydride or fumaric acid, itaconic acid or anhydride, isocyanatoethyl (meth)acrylate, dimethylaminoethyl (meth)acrylate, and 2-(5-methacryloyl-pentyl)-1,3-oxazoline.

USSN: 09/937,551

PASCAULT, Jean Pierre, et al.

4. (previously presented) The microparticles of Claim 1 wherein component B is selected from multifunctional (meth)acrylate monomers of functionality ranging from 2 to 6, substituted or unsubstituted divinylbenzenes and/or multifunctional (meth)acrylic ester oligomers or unsaturated polyesters of functionality ranging from 2 to 50 and with a number average molecular weight M_n of less than 2500.

5. (previously presented) The microparticles of Claim 1 wherein the composition of the polymerizable compounds comprises:

- 50 to 95 mol% of a component A selected from the group consisting of isobornyl (meth)acrylate, norbornyl (meth)acrylate, butyl (meth)acrylate and combinations thereof
- 0.5 to 10 mol% of a component B consisting of at least one monomer and/or oligomer selected from:
 - di(meth)acrylates of: ethylene glycol, propylene glycol, butanediol, 2-methylpropanediol, neopentyl glycol, hexanediol, diol oligomers with an M_n of less than 2500, preferably polyethers, polyesters or polyurethanes
 - substituted or unsubstituted divinylbenzenes
 - unsaturated polyester oligomers or acrylated acrylic oligomers with an M_n of less than 2500
- and having a number of ethylenic unsaturations per mole of from 2 to 50
- not more than 49.5 mol% of a component C consisting of at least one monomer and/or oligomer selected from:
 - (meth)acrylic acid, maleic, fumaric or itaconic acid, when fl is a carboxyl function;
 - maleic anhydride or itaconic anhydride when, fl is a carboxylic anhydride function;
 - hydroxyalkyl (meth)acrylates containing a C_2 - C_6 alkyl or mono (meth) acrylates of polyether or polyester or polyurethanediol or polycaprolactone oligomers with an M_n of less than 1500, when fl is a hydroxyl function;

PASCAULT, Jean Pierre, et al.

USSN: 09/937,551

glycidyl (meth)acrylate, (meth)acrylates of epoxidized derivatives of dicyclopentadiene or epoxidized vinylnorbornene (meth)acrylates or alkoxyated glycidyl ether (meth)acrylates or (meth)acrylates of epoxidized derivatives of cyclohexene, when fl is an epoxy function;

- isocyanatoethyl (meth)acrylate and urethane mono (meth) acrylates derived from diisocyanates, when fl is an isocyanate function;

- (meth)acrylates bearing a trialkyl or trialkoxysilane group, when fl is a silane function;

- dimethylaminoethyl (meth)acrylate or tert-butylaminoethyl (meth)acrylate, when fl is an amine function;

- 2-(5-(meth)acryloylpentyl)-1, 3-oxazoline, when fl is a oxazoline function;

with the sum A + B + C being equal to 100 mol%.

6. (previously presented) The microparticles according to Claim 1 wherein fl is carboxyl functions or hydroxyl functions which are partially or totally modified into functions f2 selected from the group consisting of: (meth)acrylate, vinyl, maleate, fumarate, maleimide, carboxylic acid salt or combinations thereof.

7. (previously presented) The microparticles of Claim 1 wherein they bear hydroxyl or epoxy functions fl possibly partially modified into (meth)acrylate functions f2.

8. (previously presented) A process for preparing the microparticles as defined in Claim 1, the process comprising the steps of:

- polymerizing, via radical-mediated dispersion polymerization, in a non-aqueous medium which is a nonsolvent for the polymer formed, a composition of polymerizable compounds as defined in Claim 1, without any addition of a stabilizing polymer for the microparticles formed, either before, during or after polymerization and optionally,

- chemically modifying, at least partially, the functions fl borne by the component C.

9. (previously presented) A coating, moulding or composite composition, comprising the microparticles of Claim 1.

USSN: 09/937,551

PASCAULT, Jean Pierre, et al.

10. (previously presented) The composition of Claim 9 consisting essentially of the microparticles of Claim 1 comprising functions f1 and/or f2 which are identical or different and which can be crosslinked between microparticles, forming at least one crosslinking network.
11. (previously presented) The composition of Claim 9 comprising from 0.5 to 50% by weight of the microparticles of Claim 1.
12. (previously presented) The composition of Claim 9 wherein the composition is a coating composition.
13. (previously presented) The composition according to Claim 12 wherein the coating composition is a composition which can undergo radical-mediated crosslinking, comprising: (i) acrylic or vinyl mono-or multifunctional monomers and/or multifunctional acrylic oligomers and (ii) the microparticles of Claim 1 bearing f2 functions selected from the group consisting of (meth)acrylate, maleate, fumarate, maleimide functions and combinations thereof, the f2 functions obtained from the at least partial modification of the starting functions f1.
14. (previously presented) The composition of Claim 12 wherein the coating composition is a composition which can undergo crosslinking by radiation.
15. (previously presented) The composition of Claim 13 wherein the crosslinkable composition comprises: (i) acrylic monomers selected from the group consisting of: isobornyl (meth)acrylate, isodecyl (meth)acrylate, lauryl (meth)acrylate, 2-(2-ethoxyethoxy) ethyl (meth)acrylate, tridecyl (meth)acrylate, 2-phenoxyethyl (meth)acrylate, tetrahydrofurfuryl (meth)acrylate and combinations thereof, and/or (ii) at least one acrylic oligomer chosen from the group consisting of: polyether (meth)acrylates, polyester (meth)acrylates, polyurethane (meth)acrylates, polycaprolactone (meth)acrylates, epoxy (meth)acrylates and (meth) acrylated acrylic copolymers.
16. (previously presented) The coating composition of Claim 12, characterized in that it is intended to be applied or is applied in the form of a coating on polar or non-polar substrates and comprises:
- 0.5 to 50% and preferably from 5 to 30% by weight of the microparticles of Claim 1, having f2 functions selected from the group consisting of: (meth)acrylate, maleate, fumarate, maleimide and combinations thereof,

PASCAULT, Jean Pierre, et al.

USSN: 09/937,551

- 50 to 99.5% by weight of at least one monomer chosen from: isobornyl (meth)acrylate, isodecyl (meth)acrylate; lauryl (meth)acrylate; or tridecyl (meth)acrylate,
- 0 to 5% by weight of a C₂-C₆ alkylene diol di(meth)acrylate

the percentages being chosen such that the total sum of the microparticles and monomers is equal to 100% by weight.

17. (previously presented) The coating composition according to Claim 16 wherein:

- the polar substrates are selected from the group consisting of: glass, steel, aluminium, silicon, polycarbonate, wood, glass fibres, carbon fibres, cellulose fibres, polyester or polyamide fibres;

- the non-polar substrates are selected from the group consisting of: polyolefins and more particularly polyethylene, polypropylene and ethylene/propylene copolymers with or without special surface treatment, and coatings of low surface tension.

18. (previously presented) The coating composition of Claim 16 applied to the substrate in the form of a thin film with a thickness of less than 100 microns.

19. (previously presented) The composition of Claim 12, wherein the coating composition is a composition of an aqueous dispersion of a crosslinkable polymer, comprising reactive water-dispersible or water-soluble microparticles, which participate in the crosslinking.

20. (previously presented) The coating composition of Claim 9, wherein the composition is a composition comprising epoxidized derivatives.

21. (previously presented) The coating composition of Claim 20, wherein the composition is crosslinkable by UV radiation in the presence of a cationic photo-initiator and comprises microparticles bearing epoxy and/or hydroxyl functions fl.

22. (previously presented) The coating composition of Claim 20, wherein the composition is crosslinkable by condensation reaction with at least one second reactive component selected from the group consisting of: polyamines, carboxy functionalized or carboxylic anhydride-functionalized polymers or copolymers; and combinations thereof.

23. (previously presented) The coating composition of Claim 20, when the composition can be crosslinked by condensation reaction, the composition comprising microparticles having

USSN: 09/937,551

PASCAULT, Jean Pierre, et al.

functions f1 and/or f2 selected from the group consisting of: epoxy; hydroxyl; carboxyl; anhydride; and combinations thereof.

24. (previously presented) The coating composition of Claim 9, wherein the composition comprises: (i) at least one reactive resin selected from the group consisting of: alkyds, unsaturated polyesters, saturated polyesters, polyamides, polyurethanes and polyureas and (ii) the microparticles of Claim 1.

25. (previously presented) The moulding composition of Claim 9 further comprising: (i) at least one reactive resin selected from the group consisting of: unsaturated polyesters, dicyclopentadiene resins, vinyl esters, epoxides, polyamines, polyurethanes, polyureas and polyurethane-ureas; and (ii) the microparticles of Claim 1.

26. (previously presented) The moulding composition according to Claim 25, further comprising inorganic and/or organic fillers and/or reinforcing agents chosen from the group consisting of: glass fibres, glass mats, carbon fibres, cellulose fibres, polyester and polyamide fibres.

27. (previously presented) The coating composition of Claim 24 wherein the microparticles further comprise functions f1 and/or f2 that are reactive with at least one function borne by this or these reactive resin (s).

28. (previously presented) The moulding composition of Claim 25 wherein the microparticles further comprise functions f1 and/or f2 that are reactive with at least one function borne by this or these reactive resin (s).